



## TEST REPORT

Report nr.: **1606430-001**  
Report date: **29-nov-16**  
Acceptance code: **1606430**  
Acceptance date: **21-nov-16**  
Start test date: **21-nov-16**  
End test date: **29-nov-16**  
References: **---**

Customer code: 688

To:  
**TESSITURA ATTILIO IMPERIALI SPA**  
**via Bulgaro 13**  
**22075 LURATE CACCIVIO (CO)**  
**Italia**

To the attention of:

sig. Sergio

Tel.nr: +39 031 490109

Fax.nr.: +39 031 390132

Article description: **1004T600DOA RASO IMPERIALI DOPPIATO**  
Declared composition: **72% Viscose - 28% Silk**  
End use: **Footwear**  
Typology: **Satin**  
Return: **Sample and specimens enclosed**  
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.  
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
<b>60184 DETERMINATION OF ALLERGENIC DISPERSE DYES</b>		
<b>Method:</b>	DIN 54231-2005	
<b>Instrument:</b>	TLC/LC-DAD/LC-MS	
Extraction by methanol at 70°C - 30 min into ultrasonic bath detection Limit: 5 mg/kg		
<b>RESULTS:</b>		
ALLERGENIC DISPERSE DYES - CAS nr - CONTENT		
DISPERSE BLUE 1 (2475-45-8): not detectable		
DISPERSE BLUE 3 (2475-46-9): not detectable		
DISPERSE BLUE 7 (3179-90-6): not detectable		
DISPERSE BLUE 26 (3860-63-7): not detectable		
DISPERSE BLUE 35 (12222-75-2): not detectable		
DISPERSE BLUE 102 (1222-97-8): not detectable		
DISPERSE BLUE 106 (12223-01-7): not detectable		
DISPERSE BLUE 124 (61951-51-7): not detectable		
DISPERSE BROWN 1 (23355-64-8): not detectable		
DISPERSE ORANGE 1 (2581-69-3): not detectable		
DISPERSE ORANGE 3 (730-40-5): not detectable		
DISPERSE ORANGE 37/76 (12223-33-5): not detectable		
DISPERSE RED 1 (2872-52-8): not detectable		
DISPERSE RED 11 (2872-48-2): not detectable		
DISPERSE RED 17 (3179-89-3): not detectable		
DISPERSE YELLOW 1 (119-15-3): not detectable		
DISPERSE YELLOW 3 (2832-40-8): not detectable		
DISPERSE YELLOW 9 (6373-73-5): not detectable		
DISPERSE YELLOW 39 (12236-29-2): not detectable		
DISPERSE YELLOW 49 (54824-37-2): not detectable		
DISPERSE ORANGE 149 (85136-74-9): not detectable		
DISPERSE YELLOW 23 (6373-73-5): not detectable		



Report nr.

**1606430-001**

This determination was carried out c/o an external laboratory accredited ACCREDIA N. 0529

-----  
**END OF TEST REPORT**  
-----

**Supervisor Head**

p.i. Giovanna Baglio

**Technical Head**

dott. Marco Piu